

Product name : SOLIDOIL | SOLIDNATURE **XD 3000 | XD 3094**

Description

SolidOil is a 2k water-based oil effect coating for wooden floors; it is mat and is a good toner. It is suitable for any type of wood.

SolidOilNature is a 2k water-based natural oil effect coating for wood floors; it is mat and suitable for light woods or where a whitening effect is needed.

Version

XD 3000 SolidOil | XD 3094 SolidNature

Application possibilities

They can be used on raw wood or in order to restore already treated floors.

Peculiarities

These are alkyd-urethane resin-based coatings. They are highly resistant to wear and they have particular chemical resistances, definitely superior to other oils or waxes on the market. They are elastic and contain small quantities of solvent. They contain no dangerous substances for people and nature. Its special UV filters make it not yellowing and protect the natural colour of the wood.

Application instructions

Short haired paint roller, brush.

Product preparation

Dilute at 5% with the hardener Solid 2k. For the first coat, we suggest to dilute at 5-10% with SolidLongLife or simple water.

Certifications or dry film coating properties in 2k coating system: 3 coats of SolidOil

Comply with high traffic standards according to the following norms:

- Resistant to abrasion UNI EN 15185
- Resistant to chemical agents UNI EN 13442
- Resistant to dirt UNI 9300

Chemical and physical characteristics at 23° C

Appearance	Whitish liquid
Colour	White (variable colour)
Opacity	[gloss] 5 +/- 2
pH	8 +/- 1
Specific weight	[g/ml] 1,01 +/- 0,03
Chemical nature	Alkyd poliurethane aliphatic
Viscosity	[s] (23°C; cup DIN hole 4) 16 +/- 5
Viscosity of the catalysed coating	[s] (23°C; cup DIN hole 4) 17 +/- 5

Application specifics

Number of coat suggested	2-3
Quantity per coat suggested	[g/m ²] min. 40; max. 80
Duration of the blend	[hours] min. 4
Wait time between coats	[hours] 2-6
Yield per coat	[m ² /L] 7-9
Application temperature	[°C] between +10 and +35
Slight foot traffic	[hours] 4
Intense foot traffic	[hours] 24
Livable after	[days] 2

Surface preparation

Carefully clean the wood surface. Plaster the grout lines with SolidFiller blended with sawdust obtained from floor sanding. Once dried, sand the raw wood (grit 100-150 suggested) and clean it from grease, wax or glue. Clean the floor with a vacuum before coating. If you paint a surface already coated, use a water insoluble colour in order to prevent the discoloration of the surface.

Application instructions

Mix well in order to homogenize any eventual sediment on the bottom. Apply the product adding 5% of Solid2k while stirring and mixing vigorously for one minute. On dry wood and, in particular, in summer, dilute the first coat with 10% of SolidLongLife or water.

Wait at least 6 hours before sanding with a paper 220-280 grit, or with mechanical tools with sand paper grit 320-360. Vacuum-clean and, then, apply the second coat diluted at 5% with Solid2k.

If needed, apply a third coat, without sanding, waiting 2-3 hours between coats.

It is possible to walk carefully on the coated surface after 16 hours. The right hardness can be reached in one week.

It is preferable to wait at least 48 hours from the last coat application before putting furniture inside of the coated space.

Catalysis

After the addition, apply it within 4 hours maximum (3 hours during summer). After that time it is necessary to prepare it again.

Application conditions

Ambient temperature. Apply between 10°C and 35°C. The right temperature is between 15°C and 25°C.

Ambient humidity between 40% and 80%.

Foundation humidity. Minimum content allowed = 10% measured with hygrometer.

Suggested coating systems

In order to preserve the colour of light woods, apply two or three coats of SolidOilNature following the pertinent application instructions.

On dark woods or to obtain a good wood tone, apply one or two coats of SolidOil following the pertinent application instructions.

Preexisting wooden surfaces

After checking the right glueing of the floor to the base, sand it in order to remove the coated or polished surface film and vacuum-clean the surface.

Cleaning of pre-finished wood floors previously coated with SolidZero

From not dried adhesive traces: remove carefully the adhesive with a cleaned cloth, wadding or soft paper. If the surface looks altered, lightly blot up with a cleaned cloth or with wadding dampen with SolidClean.

From dried adhesive traces: remove carefully with a nail or a piece of rigid plastic the eventual imperfections.

Never use blades, metal or sharp-cornered objects. If the surface looks altered, lightly blot up with a cleaned cloth or with wadding dampen with SolidClean. Always test beforehand any other cleaner in order to verify the compatibility with the wood floor surface, using a wooden board, in order to prevent surface damages.

Tools cleaning

Clean every tool immediately after use. The product can be easily removed with water from the paint roller or the brush.

Waste disposal

The exceeding and useless material, along with the washing water must be disposed of as special waste. Do not empty into drains.

Personal protective equipment

Wear protective rubber, latex or polyethylene gloves. It can release in the air small amounts of solvent. Please, ventilate the room during the application.

Package

5 L tanks

Storage

The product keeps inalterated its characteristics throughout 18 months if stored inside its original package, tightly closed, at 23° C. Do not store in damp or wet places at temperatures exceeding 35° C.

Packaging recycling

The plastic package must be recycled in the right dumper or recycling point (according to the local garbage collection). Please, check if the package is empty and dry, with the minimum possible product quantity inside.

Warnings

Data and information inside this Technical Sheet represent our current best knowledge and experiences and cannot be used as a warranty due to the diversity of materials existing on the market and the difficult monitoring of application conditions.

The final user must check if the product corresponds to his own needs in relation to application tools, supports and environmental conditions of application and drying. In any case, Renner Italia S.p.A. guarantees the constant quality of its products. Renner Italia S.p.A. reserves the right to modify and update this technical sheet according to its own needs. Customers shall verify to own the updated version of this sheet.

CAREFULLY READ AND UNDERSTAND THIS TECHNICAL SHEET BEFORE USING THE PRODUCT

